


Safety data sheet according to 1907/2006/EC

Printing date 06.08.2021

Version number 2 (replaces version 1)

Revision: 06.08.2021



- · Signal word Void
- · Hazard statements Void
- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · **PBT:** Not applicable.
- **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

- · 3.2 Mixtures
- · Description:

Mixture of substances listed below with nonhazardous additions according to Regulation (EC) No 1272/2008. Sodium acetate CAS 6131-90-4

Water CAS 7732-18-5

- · Dangerous components: Void
- · SVHC Not applicable.
- Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

• 4.1 Description of first aid measures

- · General information: Immediately remove any clothing soiled by the product.
- After inhalation: Supply fresh air; consult doctor in case of complaints.
- After skin contact: If skin irritation continues, consult a doctor.

(Contd. on page 2)



Safety data sheet according to 1907/2006/EC

Version number 2 (replaces version 1)

Revision: 06.08.2021

(Contd. of page 1)

Trade name: Testomat Chlor Reagenz AM

- After eye contact: Rinse opened eye for several minutes under running water. • After swallowing:
- Rinse out mouth and then drink plenty of water.
- Seek medical treatment. A person vomiting while laying on their back should be turned onto their side.
- 4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.
- **4.3 Indication of any immediate medical attention and special treatment needed** No further relevant information available.

SECTION 5: Firefighting measures

- [·] 5.1 Extinguishing media
- Suitable extinguishing agents: Use fire extinguishing methods suitable to surrounding conditions.
- **5.2 Special hazards arising from the substance or mixture** In case of fire, the following can be released: Acetic acid
- 5.3 Advice for firefighters
- · Protective equipment: Wear self-contained respiratory protective device.

SECTION 6: Accidental release measures

- **6.1 Personal precautions, protective equipment and emergency procedures** Wear personal protection equipment.
- **6.2 Environmental precautions:** Dilute with plenty of water.
- 6.3 Methods and material for containment and cleaning up: Clean the affected area carefully; suitable cleaners are: Warm water

Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).

6.4 Reference to other sections

See Section 7 for information on safe handling.

See Section 8 for information on personal protection equipment.

See Section 13 for disposal information.

SECTION 7: Handling and storage

- 7.1 Precautions for safe handling No special measures required.
- · Information about fire and explosion protection: No special measures required.

· 7.2 Conditions for safe storage, including any incompatibilities

- · Storage:
- · Requirements to be met by storerooms and receptacles: Store only in the original receptacle.
- · Information about storage in one common storage facility: Store away from foodstuffs.
- · Further information about storage conditions:
- Keep container tightly sealed. Protect from heat and direct sunlight.
- Store receptacle in a well ventilated area.
- · Recommended storage temperature: 15 25 °C

• Storage class:

- Storage class 12: Non-combustible liquids that cannot be assigned to any other storage class (TRGS 510)
- **7.3 Specific end use(s)** No further relevant information available.

_____ DE_EN-(Contd. on page 3)



Safety data sheet according to 1907/2006/EC

Version number 2 (replaces version 1)

Revision: 06.08.2021

Trade name: Testomat Chlor Reagenz AM

(Contd. of page 2)

Control parameters redients with limit values that require monitoring at the product does not contain any relevant quantities of mate itored at the workplace. Ilitional information: The lists valid during the making we Exposure controls propriate engineering controls No further data; see item vidual protection measures, such as personal protect meral protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. mediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mi d protection ar gloves according to EN 374. glove material has to be impermeable and resistan naration. ection of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etrain of gloves selection time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties information on basic physical and chemical properties priore formation is a physical and chemical propertis priore	
product does not contain any relevant quantities of mate itored at the workplace. Ilitional information: The lists valid during the making we Exposure controls propriate engineering controls No further data; see item vidual protection measures, such as personal protect propriate engineering controls No further data; see item vidual protection measures, such as personal protect protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. rediately remove all solled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mid ar gloves according to EN 374. glove material has to be impermeable and resistan paration. ection of the glove material on consideration of the penetra radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) frace protection Goggles according to EN 166 recomme by protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties protection from the physical and chemical properties protection from the physical and chemical properties protection fon the splo	
Itional information: The lists valid during the making we Exposure controls propriate engineering controls No further data; see item vidual protection measures, such as personal protect paral protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. mediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mid of protection ar gloves according to EN 374. glove material has to be impermeable and resistan naration. ection of the glove material on consideration of the penetradation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties the permetion: Protective work clothing	ials with critical values that have to
Exposure controls propriate engineering controls No further data; see item vidual protection measures, such as personal protection paway from foodstuffs, beverages and feed. mediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mid d protection ar gloves according to EN 374. glove material has to be impermeable and resistant naration. ection of the glove material on consideration of the penel radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. ettration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection Goggles according to EN 166 recomme ty protection: Protective work clothing <i>CTION 9: Physical and chemical properties</i> Information on basic physical and chemical properties protection on basic physical and chemical properties	
propriate engineering controls No further data; see item vidual protection measures, such as personal protection peral protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. hediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mi of protection ar gloves according to EN 374. glove material has to be impermeable and resistan paration. ection of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper con ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permeant contact gloves made of the following if rubber, NBR ommended thickness of the material: ≥ 0.12 mm ie for the permeation: Level = 6 (> 480 min) protection Goggles according to EN 166 recomme ty protection. Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties and chemical properties	re used as basis.
vidual protection measures, such as personal protection peral protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. mediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mit and protection ar gloves according to EN 374. glove material has to be impermeable and resistan baration. action of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le for the permeation: Level = 6 (> 480 min) protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties	
neral protective and hygienic measures: usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. rediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mi- ad protection ar gloves according to EN 374. glove material has to be impermeable and resistan baration. action of the glove material on consideration of the penetri radation ck protective gloves prior to each use for their proper com- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) face protection Goggles according to EN 166 recomme by protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties	
usual precautionary measures are to be adhered to when p away from foodstuffs, beverages and feed. hediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mi dd protection ar gloves according to EN 374. glove material has to be impermeable and resistan baration. action of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper con ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. tetration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) face protection Goggles according to EN 166 recomme by protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties	ive equipment
p away from foodstuffs, beverages and feed. nediately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mi- ad protection ar gloves according to EN 374. glove material has to be impermeable and resistan paration. bettion of the glove material on consideration of the penel radation ck protective gloves prior to each use for their proper com- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. the permanent contact gloves made of the following is rube observed. the permanent contact gloves made of the following is rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following is rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following is rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) (face protection Goggles according to EN 166 recomme by protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties protection from splashes ployees made of the following the permeation: Level = 6 (> 480 min) (face protection: Protective work clothing CTION 9: Physical and chemical properties protection: Protective work clothing	
The diately remove all soiled and contaminated clothing sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mind protection ar gloves according to EN 374. glove material has to be impermeable and resistan baration. Action of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following is rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following is rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) (face protection Goggles according to EN 166 recomme ty protection : Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties	nandling chemicals.
sh hands before breaks and at the end of work. not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mind protection ar gloves according to EN 374. glove material has to be impermeable and resistan paration. action of the glove material on consideration of the penel radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties partice permeation:	
not eat, drink, smoke or sniff while working. piratory protection: suitable respiratory protective device when aerosol or mind protection ar gloves according to EN 374. glove material has to be impermeable and resistan paration. action of the glove material on consideration of the penel radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties perial Information	
piratory protection: suitable respiratory protective device when aerosol or mind protection ar gloves according to EN 374. glove material has to be impermeable and resistant paration. action of the glove material on consideration of the penetra radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) orotection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) orotection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
suitable respiratory protective device when aerosol or mind protection ar gloves according to EN 374. glove material has to be impermeable and resistan baration. action of the glove material on consideration of the pener radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) orotection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) orotection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
ar gloves according to EN 374. glove material has to be impermeable and resistan paration. action of the glove material on consideration of the pener radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. tetration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties the formation	st is formed. Filter: Type P2
glove material has to be impermeable and resistan paration. action of the glove material on consideration of the pener radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. retration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) Aface protection Goggles according to EN 166 recomme by protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
paration. action of the glove material on consideration of the pener radation the protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. retration time of glove material exact break through time has to be found out by the mat- to be observed. the permanent contact gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm ie for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm ie for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm ie for the permeation: Level = 6 (> 480 min) Aface protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	, , , , , , , , , , , , , , , , , , ,
ection of the glove material on consideration of the penet radation ck protective gloves prior to each use for their proper conventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the material to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) (face protection Goggles according to EN 166 recomme by protection: Protective work clothing (face protection: Protective work clothing) (face protection: Protective work clothing) (face protection: Protective work clothing)	to the product/ the substance/
radation ck protective gloves prior to each use for their proper con- ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the main to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	ration timon rates of diffusion and
ck protective gloves prior to each use for their proper con ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. retration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties the formation	ration limes, rates of diffusion and
ventive skin protection by use of skin-protecting agents is r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme fly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	dition
r use of gloves apply skin-cleaning agents and skin cosm erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following the rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
erial of gloves selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm te for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
selection of the suitable gloves does not only depend on uality and varies from manufacturer to manufacturer. etration time of glove material exact break through time has to be found out by the ma- to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm to for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm to for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme fly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
etration time of glove material exact break through time has to be found out by the mat to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm to for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm to for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	the material, but also on further ma
exact break through time has to be found out by the main to be observed. the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
to be observed. the permanent contact gloves made of the following lie rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the followin lie rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) / face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties Information	• · • • · · · ·
the permanent contact gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following of rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	iufacturer of the protective gloves
ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following ile rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	matarials are suitable:
ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	nateriais are suitable.
The for the permeation: Level = 6 (> 480 min) protection from splashes gloves made of the following the rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ty protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
protection from splashes gloves made of the following le rubber, NBR ommended thickness of the material: ≥ 0.12 mm ue for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical properties peral Information	
ommended thickness of the material: ≥ 0.12 mm le for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical propertie peral Information	y materials are suitable:
te for the permeation: Level = 6 (> 480 min) /face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical propertie peral Information	
/face protection Goggles according to EN 166 recomme ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical propertie peral Information	
ly protection: Protective work clothing CTION 9: Physical and chemical properties Information on basic physical and chemical propertie peral Information	e de destruis en la Cillia e
CTION 9: Physical and chemical properties Information on basic physical and chemical propertienter of the proper	ided during refilling
Information on basic physical and chemical propertie peral Information	
Information on basic physical and chemical propertie peral Information	
neral Information	
neral Information	5
sical state Fluid	
our: Colourless	
our: Characteris	
bur threshold: Not determine	
ting point/freezing point: Undetermin	<i>≩</i> α.
ling point or initial boiling point and ing range Undetermin	a d
ing range Undetermin	111



Safety data sheet according to 1907/2006/EC

Version number 2 (replaces version 1)

Revision: 06.08.2021

Trade name: Testomat Chlor Reagenz AM

	(Contd. of page
Flammability	Not applicable.
Lower and upper explosion limit	
Lower:	Not determined.
Upper:	Not determined.
Flash point:	Undetermined.
Auto-ignition temperature:	Product is not selfigniting.
Decomposition temperature:	Not determined.
pH (100 g/l) at 20 °C	5.8
Viscosity:	
Kinematic viscosity	Not determined.
Dynamic:	Not determined.
Solubility	
water:	Fully miscible.
Partition coefficient n-octanol/water (log	
value)	Not determined.
Vapour pressure:	Not determined.
Density and/or relative density	
Density at 20 °C:	1.06 g/cm³
	Not determined.
Relative density Vapour density	Not determined.
	Not determined.
Ignition temperature: Explosive properties:	Product does not present an explosion hazard.
	Froudel does not present an explosion nazard.
Change in condition Evaporation rate	Not determined.
Change in condition Evaporation rate Information with regard to physical haza	Not determined.
Change in condition Evaporation rate Information with regard to physical haza classes	Not determined.
Change in condition Evaporation rate Information with regard to physical haza classes Explosives	Not determined. rd Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases	Not determined. rd Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols	Not determined. rd Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases	Not determined. rd Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure	Not determined. rd Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure	Not determined. rd Void Void Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids	Not determined. rd Void Void Void Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids	Not determined. rd Void Void Void Void Void Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures	Not determined. rd Void Void Void Void Void Void Void Void Void Void Void Void
Change in condition Evaporation rate Information with regard to physical haza	Not determined. rd Voi
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids	Not determined. rd Voi
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures	Not determined. rd Voi
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit	Not determined. rd Voi
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water	Not determined. rd Voi
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids	Not determined. rd Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids Oxidising solids	Not determined. rd Void
Change in condition Evaporation rate Information with regard to physical haza classes Explosives Flammable gases Aerosols Oxidising gases Gases under pressure Flammable liquids Flammable solids Self-reactive substances and mixtures Pyrophoric liquids Pyrophoric solids Self-heating substances and mixtures Substances and mixtures, which emit flammable gases in contact with water Oxidising liquids	Not determined. rd Void

SECTION 10: Stability and reactivity

• **10.1 Reactivity** No further relevant information available.

· 10.2 Chemical stability

· Thermal decomposition / conditions to be avoided:

No decomposition if used according to specifications.

10.3 Possibility of hazardous reactions No dangerous reactions known.

(Contd. on page 5)



Safety data sheet according to 1907/2006/EC

Version number 2 (replaces version 1)

Revision: 06.08.2021

Trade name: Testomat Chlor Reagenz AM

(Contd. of page 4)

- **10.4 Conditions to avoid** No further relevant information available.
- **10.5 Incompatible materials:** No further relevant information available.

· 10.6 Hazardous decomposition products: Acetic acid

SECTION 11: Toxicological information

- \cdot 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008
- Acute toxicity Based on available data, the classification criteria are not met.
- Skin corrosion/irritation Based on available data, the classification criteria are not met.
- Serious eye damage/irritation Based on available data, the classification criteria are not met.
- Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- Germ cell mutagenicity Based on available data, the classification criteria are not met.
- Carcinogenicity Based on available data, the classification criteria are not met.
- Reproductive toxicity Based on available data, the classification criteria are not met.
- STOT-single exposure Based on available data, the classification criteria are not met.
- **STOT-repeated exposure** Based on available data, the classification criteria are not met. • **Aspiration hazard** Based on available data, the classification criteria are not met.

11.2 Information on other hazards

· Endocrine disrupting properties

None of the ingredients is listed.

SECTION 12: Ecological information

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- · 12.3 Bioaccumulative potential No further relevant information available.
- 12.4 Mobility in soil No further relevant information available.
- 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- · vPvB: Not applicable.
- 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

- 12.7 Other adverse effects
- · Additional ecological information:
- · General notes:

Water hazard class 1 (German Regulation) (Self-assessment): slightly hazardous for water Do not allow undiluted product or large quantities of it to reach ground water, water course or sewage system.

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation Disposal must be made according to official regulations.

- · Uncleaned packaging:
- · Recommendation:

Packagings that may not be cleansed are to be disposed of in the same manner as the product. Disposal must be made according to official regulations.

• Recommended cleansing agents: Water, if necessary together with cleansing agents.

(Contd. on page 6)

DE EN



Safety data sheet according to 1907/2006/EC

Printing date 06.08.2021

Version number 2 (replaces version 1)

Revision: 06.08.2021

Trade name: Testomat Chlor Reagenz AM

(Contd. of page 5)

SECTION 14: Transport information	tion
[·] 14.1 UN number or ID number [·] ADR, IMDG, IATA	Void
· 14.2 UN proper shipping name · ADR, IMDG, IATA	Void
· 14.3 Transport hazard class(es)	
· ADR, ADN, IMDG, IATA · Class	Void
· 14.4 Packing group · ADR, IMDG, IATA	Void
[.] 14.5 Environmental hazards: [.] Marine pollutant:	No
[.] 14.6 Special precautions for user	Not applicable.
 14.7 Maritime transport in bulk accordi IMO instruments 	ng to Not applicable.
· Transport/Additional information:	Not dangerous according to the above specifications.
· UN "Model Regulation":	Void

SECTION 15: Regulatory information

 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

· Directive 2012/18/EU

- · Named dangerous substances ANNEX I None of the ingredients is listed.
- DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II

None of the ingredients is listed.

· REGULATION (EU) 2019/1148

 Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))

None of the ingredients is listed.

• Annex II - REPORTABLE EXPLOSIVES PRECURSORS None of the ingredients is listed.

· National regulations:

• Technical instructions (air):

 Class
 Share in %

 //
 0.5

• Waterhazard class: Water hazard class 1 (Self-assessment): slightly hazardous for water.

• 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship. (Contd. on page 7)

DE_EN-



Safety data sheet according to 1907/2006/EC

Version number 2 (replaces version 1)

Revision: 06.08.2021

Trade name: Testomat Chlor Reagenz AM

	(Contd. of page
Ľ	Department issuing SDS: product safety department
	Date of previous version: 14.01.2021
	/ersion number of previous version: 1
	Abbreviations and acronyms:
F	RD: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulatio Concerning the International Transport of Dangerous Goods by Rail)
10	CAO: International Civil Aviation Organisation
	ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agreement Concern he International Carriage of Dangerous Goods by Road)
	MDG: International Maritime Code for Dangerou's Goods
	ATA: International Air Transport Association
	GHS: Globally Harmonised System of Classification and Labelling of Chemicals
	EINECS: European Inventory of Existing Commercial Chemical Substances
	ELINCS: European List of Notified Chemical Substances
	CAS: Chemical Abstracts Service (division of the American Chemical Society)
F	PBT: Persistent, Bioaccumulative and Toxic
S	SVHC: Substances of Very High Concern
V	PvB: very Persistent and very Bioaccumulative
*	Data compared to the previous version altered.